

Vistamaxx™ 8780

Performance Polymer

Product Description

Vistamaxx 8780 is primarily composed of isotactic propylene repeat units with random ethylene distribution, and is produced using ExxonMobil's proprietary metallocene catalyst technology. It has very low viscosity that enables its use in hot melt adhesives (HMAs) and as a process aid or viscosity modifier in extrusion and injection molding applications providing enhanced flow characteristics that can lead to efficiency and cycle time improvements.

Key Features

- Low density
- Very low viscosity
- Low odor and low color
- Non-corrosive

General

Availability ¹	▪ Africa & Middle East ▪ Asia Pacific	▪ Europe ▪ Latin America	▪ North America
Applications	▪ Hot Melt Adhesives	▪ Polymer Modification	
Uses	▪ Adhesives	▪ Compounding	
Form(s)	▪ Pellets		
Processing Method	▪ Compounding	▪ Extrusion	▪ Injection Molding
Revision Date	▪ 01/08/2019		

Physical	Typical Value (English)	Typical Value (SI)	Test Based On
Density ²	0.864 g/cm ³	0.864 g/cm ³	ExxonMobil Method
Ethylene Content ²	12 wt%	12 wt%	ExxonMobil Method
Viscosity @ 374°F (190°C)	3980 cP	3980 mPa·s	ExxonMobil Method

Hardness	Typical Value (English)	Typical Value (SI)	Test Based On
Durometer Hardness (Shore C)	17	17	ASTM D2240

Mechanical	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Break	350 psi	2.4 MPa	ExxonMobil Method
Tensile Stress at 100%	260 psi	1.8 MPa	ExxonMobil Method
Elongation at Break	705 %	705 %	ExxonMobil Method

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Melting Temperature	205 °F	96 °C	ExxonMobil Method
Glass Transition, T _g	-26 °F	-32 °C	ExxonMobil Method

Additional Information

For handling and safety information, consult the appropriate Safety Data Sheet.

ExxonMobil Test Methods, some of which were developed from ASTM test methods, are available upon request.

It is the responsibility of the user to ensure that the composition containing our product meets the limitations of relevant regulations. Please contact Customer Service for the official food law certificates which provide more detailed information.

Legal Statement

This product, including the product name, shall not be used or tested in any medical application without the prior written acknowledgement of ExxonMobil Chemical as to the intended use. For detailed Product Stewardship information, please contact Customer Service.

Vistamaxx™ 8780
Performance Polymer**Processing Statement**

Vistamaxx polymers have a wide temperature processing window. A good starting point for temperatures is 10°C above the highest melting point. This material does not require drying and can be compounded or used in a dry blend. Use conventional processing knowledge to ensure mixing of the materials.

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

² Property specified in conventional unit of measure.

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2019 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Chemical" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com